

R210-8 Black Closed Cell Neoprene Sponge:

<i>PROPERTIES</i>	<i>AVERAGE VALUE</i>
ASTM D1056 - 00	2C2
Density	140 Kg m ³
Compression Deflection 25% (35-63)	47 kPa
Compression Set 50% 22/h 20°C (25% Max.)	22 %
Elongation – ASTM D412	170%
Temperature Range (Constant)	- 40°C / + 85°C
Water Absorption	0.005%
Tensile Strength (Kg/cm ³) – ASTM D412	6.2
Heat Ageing – Change in compression deflection 168 hrs @ 70°C - ±30%	18%
Fire Resistance – FMVSS 302 (Burn Rate <100mm)	Pass

*The above figures are average values.
We recommend evaluation prior to use to ascertain the suitability of the material for the application.*